

TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- ALUMINIUM WOOD PRIMER

REFERENCE:- P/224/2

COLOUR:- GREY

FINISH:- SEMI-MATT

TYPE:- MODIFIED ALKYD, CONTAINS
FLAKE ALUMINIUM

TYPICAL SG:- 1.30 @ 20°C

TYPICAL VISCOSITY:- 3.0 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 66.5% BY WEIGHT

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- V/607/14 (WHITE SPIRIT OR
TURPS SUBS)

APPLICATION:- BRUSH, ROLLER OR SPRAY

*COVERAGE GUIDE:- 9 SQ. METRES PER LITRE

*DRYING TIME:- SURFACE DRY - 3 HOURS
THROUGH DRY - 8 HOURS

USES:- AS A HIGH QUALITY PRIMER
FOR ALL TIMBERS. RESISTS
RESIN STAINING AND
BLISTERING

HEALTH & SAFETY:- SEE SHEET HSD 'A'

*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

COO-VAR

PAINTS, PRIMERS & SPECIALISED COATINGS

Ellenshaw Works, Lockwood Street, HULL. HU2 OHN
Telephone : 01482-328053 Fax: 01482-219266