

TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- SILICONISED TEAK OIL

REFERENCE:- V/601/28

COLOUR:- CLEAR

FINISH:- TRANSPARENT

TYPE:- MODIFIED NATURAL OIL

TYPICAL SG:- 0.87 @ 20°C

TYPICAL VISCOSITY:- 16 SECS. BS1733 FLOW CUP @ 25°C

TYPICAL TOTAL SOLIDS:- 40.0%

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- WHITE SPIRIT (TURPS SUBS)

APPLICATION:- BY BRUSH

*COVERAGE GUIDE:- DIFFICULT TO ESTIMATE -
INTENDED TO "FEED" TIMBER,
DEPENDING UPON POROSITY, 7
SQ. METRES PER LITRE.

*DRYING TIME:- SURFACE DRY - 8 HOURS
THROUGH DRY -24 HOURS

USES:- AS A PROTECTIVE TO TEAK AND
SIMILAR HARD WOODS, GIVING
AN "OILED" APPEARANCE

HEALTH & SAFETY:- SEE SHEET HSD 'A2'

*BY BRUSH TO A DRIED FILM THICKNESS OF 15-20 MICRONS AT 20°C.



PAINTS, PRIMERS & SPECIALISED COATINGS

Ellenshaw Works, Lockwood Street, HULL. HU2 OHN
Telephone : 01482-328053 Fax: 01482-219266