

# TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- CHLORINATED RUBBER PAINT

REFERENCE:- G/149/1

COLOUR:- WHITE,BLACK,BLUE 18.E.51  
OTHER COLOURS TO SPECIAL  
ORDER

FINISH:- GLOSS

TYPE:- CHLORINATED RUBBER

TYPICAL SG:- 1.23 @ 20°C

TYPICAL VISCOSITY:- 3.0 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 52.2% BY WEIGHT

TYPICAL FLASH POINT:- 40°C

RECOMMENDED THINNERS:- V/607/17

APPLICATION:- BY BRUSH OR AIRLESS SPRAY

\*COVERAGE GUIDE:- 11 SQ. METRES PER LITRE

\*DRYING TIME:- SURFACE DRY - 2 HOURS  
THROUGH DRY - 24 HOURS

HEALTH & SAFETY:- SEE SHEET HSD 'K'

\*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

## Teamac® Paints

MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL  
COATINGS

Teal & Mackrill Limited,  
Lockwood Street, HULL. HU2 OHN  
Telephone: 01482-320194 Fax: 01482-219266