

# TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- DECK PAINT RED

REFERENCE:- G/150/65

COLOUR:- RED

FINISH:- GLOSS

TYPE:- MODIFIED ALKYD

TYPICAL SG:- 1.17 @ 20°C

TYPICAL VISCOSITY:- 3.5 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 65.5% BY WEIGHT

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- WHITE SPIRIT OR TURPS SUBS

APPLICATION:- BY BRUSH,ROLLER OR SPRAY

\*COVERAGE GUIDE:- 11 SQ. METRES PER LITRE

\*DRYING TIME:- SURFACE DRY 5 HOURS  
HARD DRY 24 HOURS

USES:- AS AN ECONOMICAL PROTECTIVE  
PAINT FOR DECKS WHEN APPLIED  
TO PROPERLY PREPARED  
SURFACES. DRIES TO A DURABLE  
MID GLOSS FINISH.

HEALTH & SAFETY:- SEE SHEET HSD A'

\*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

## Teamac® Paints

MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL  
COATINGS

Teal & Mackrill Limited,  
Lockwood Street, HULL. HU2 OHN  
Telephone: 01482-320194 Fax: 01482-219266