

TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- NON-SLIP DECK PAINT

REFERENCE:- G/139/

COLOUR:- RED, WHITE, BLACK, GREY, BLUE,
GREEN, YELLOW, LIGHT GREY

FINISH:- GLOSS - GRANULATED

TYPE:- MODIFIED ALKYD

TYPICAL SG:- 1.50 @ 20°C

TYPICAL VISCOSITY:- 6.0 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 77.5% BY WEIGHT
59.0% BY VOLUME

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- WHITE SPIRIT OR TURPS SUBS

APPLICATION:- BY BRUSH OR ROLLER

*COVERAGE GUIDE:- 8 SQ. METRES/LITRE

*DRYING TIME:- 4 HOURS SURFACE DRY
12 HOURS THROUGH DRY

USES:- AS A SAFETY COATING IN
AREAS WHERE A SURE
FOOTHOLD IS REQUIRED.

HEALTH & SAFETY:- SEE SHEET HSD 'A1'

*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

Teamac® Paints

**MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL
COATINGS**

Teal & Mackrill Limited,
Lockwood Street, HULL. HU2 OHN
Telephone: 01482-320194 Fax: 01482-219266