

# TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- PENETRATING WOOD PRIMER

REFERENCE:- P/224/1

COLOUR:- WHITE (PINK ALSO AVAILABLE)

FINISH:- SEMI MATT

TYPE:- MODIFIED ALKYD

TYPICAL SG:- 1.5 @ 20°C

TYPICAL VISCOSITY:- 3.0 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 72% BY WEIGHT

FLASH POINT:- 40°C

RECOMMENDED THINNERS:- WHITE SPIRIT OR TURPS SUBS

APPLICATION:- BY BRUSH OR SPRAY

\*COVERAGE GUIDE:- 9 SQ. METRES PER LITRE

\*DRYING TIME:- SURFACE DRY IN 3 HOURS  
THROUGH DRY IN 8 HOURS

USES:- AS A PRIMER FOR WOOD,  
PARTICULARLY SOFT WOOD.

HEALTH & SAFETY:- SEE SHEET HSD 'A'

\*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.  
DEPENDING ON POROSITY OF WOOD

## Teamac® Paints

MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL  
COATINGS

Teal & Mackrill Limited,  
Lockwood Street, HULL. HU2 OHN  
Telephone: 01482-320194 Fax: 01482-219266