

# TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- YACHT & SEAPLANE VARNISH

REFERENCE:- V/601/27

COLOUR:- CLEAR

FINISH:- FULL GLOSS

TYPE:- MODIFIED ALYKD

TYPICAL SG:- 0.92 @ 20°C

TYPICAL VISCOSITY:- 2.5 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 54.0% BY WEIGHT

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- WHITE SPIRIT (TURPS SUBS)

APPLICATION:- BY BRUSH

\*COVERAGE GUIDE:- 14 SQ. METRES/LITRE

\*DRYING TIME:- SURFACE DRY - 4-6 HOURS  
THROUGH DRY -24 HOURS

USES:- AS A HIGH BUILD FINISH FOR  
SUITABLY PREPARED AND  
SEALED TIMBER. CAN ALSO BE  
USED AS A VARNISH TO GIVE  
PROTECTION & HIGHER GLOSS  
TO EXISTING PAINTWORK.

HEALTH & SAFETY:- SEE SHEET HSD 'A'

\*BY BRUSH TO A DRIED FILM THICKNESS OF 15-20 MICRONS AT 20°C.

## Teamac® Paints

MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL  
COATINGS

Teal & Mackrill Limited,  
Lockwood Street, HULL. HU2 OHN  
Telephone: 01482-320194 Fax: 01482-219266