

TECHNICAL DATA SHEET

TDS: TMQ2714
539/Q271/4

DANISH OIL

DESCRIPTION:

Teamac Danish Oil is a hard, durable, water resistant seal for the enhancement of interior and exterior wood. Contains tung oil.

RECOMMENDED USE:

Teamac Danish Oil is ideal for use on mahogany, teak and most other timbers. Can be used for kitchen worktops, wooden panels, garden furniture and doors. Ideal to provide a more natural appearance on timber.

AVAILABILITY:

0.5 litre, 1 litre, 2.5 litre

FINISH:

Slight gloss

COLOUR:

Clear

TYPICAL S.G. (SPECIFIC GRAVITY):

0.9 @ 20 °C

VOLUME SOLIDS:

47.5%

WET FILM THICKNESS W.F.T

70 microns

DRY FILM THICKNESS D.F.T

35 microns

EXPECTED SPREADING RATE:

14 sq.m / litre

@ 35 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

124s sec . B3 cup @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 4 hours @ 20 °C

Hard dry: 8 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours / overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

433 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or lint
free cloth

Thinner Thinners 14 (5%)
(Max vol):

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Thinner 14
solvent:

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: info@teamac.co.uk

www.teamac.co.uk

Recoat interval: 12 hours / overnight

SURFACE PREPARATION:

Ensure the surface is clean, dry and free from wax, oil, grease and dirt. Use sandpaper to remove any unwanted old coatings and paints.

MIXING INSTRUCTIONS:

Mix well before use

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Teamac Danish Oil direct to prepared wood.

SUBSEQUENT COAT:

Teamac Danish Oil

REMARKS:**HEALTH AND SAFETY:**

See safety data sheet - SDS 11369

ISSUED:

23 May 2012

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 320194.

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: info@teamac.co.uk

www.teamac.co.uk